



FNCH-1 丙烯酸道路标线涂料

FNCH-1 Acrylic Road Marking Paint

产品特性 Characteristics	干燥迅速、附着力好、耐紫外线性能优良 Fast drying, good adhesion, excellent resistance to UV 具有较好的户外耐久性，可以在较低的温度下施工 Good outdoor durability, lower temperature application 耐磨性优异 Excellent abrasion resistance	
产品用途 Uses	主要用于道路、水泥或沥青马路表面划线及涂饰标志。 Mainly used as traffic line or marking paints of roads, cement or asphalt road surfaces.	
颜色 Color	白、黄、各色 White, yellow or all colors	
施工条件 Equipment	无气喷涂 airless spray 喷嘴尺寸 nozzle orifice 压力 nozzle pressure 稀释比率 thinning ratio 适用于常规的喷涂、刷涂和辊涂	推荐 recommended 0.4~0.5mm 100~150kg/cm ² 0~3% (重量比) by weight May be applied by spray, brush, or roller.
稀释剂 Thinner	丙烯酸道路标线涂料配套稀释剂 Matching thinner	
混合比率 Mixing ratio	单组分 One component	
涂装膜厚 Film thickness	干膜: 80μm/道 湿膜: 125μm/道 Dry film thickness: 80μm/coat Wet film thickness: 125μm/coat	
固体含量 Solid content	60% 60%	
比重 Specific gravity	1.4 1.4	



涂覆率 Coverage rate	理论值 : 0.25 千克/平方米/80 μ m Theoretical: 0.25 kg/m ² /80 μ m	0.179L/平方米/80 μ m 0.179L/m ² /80 μ m
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.	

干燥时间 Drying time	温度 (temperature):	10°C	20°C	30°C
	指触干燥(dry to touch) :	25mins	15mins	10mins
	实干(dry to handle):	1hrs	0.75hrs	0.5hrs

涂装间隔 Coating interval	Min. 最小	2hrs	1hrs	1hrs
	Max. 最大	—	—	—

储存期限 Shelf life	一年 12 months
--------------------	-----------------

包装规格 Packing	单组份包装: 20kg/桶 One component : 20kg /bucket
-----------------	---

表面处理 Surface preparation	彻底清洁路面, 必须保证无灰尘杂土, 保持表面干燥 Thoroughly clean the road surface free of dust and miscellaneous soil, and keep the surface dry.
	施工前充分搅匀 Stir well before application.
	施工后应维护半小时至一小时后, 才可投入使用 Maintain half to one hour after application prior to use.
	严禁混入水份, 雨天、风尘条件下不得施工 It is forbidden to be mixed with water. Do not apply under rain, wind and dust .

涂装配套 Coating system	适用底材: 水泥、沥青路面。如有任何疑问请向津海公司查询 Preferable substrates: cement or asphalt road. If you have any doubt, please refer to JINHAI PAINTS.
------------------------	--

安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention.
------------------------------	---



保证良好的通风。
Assure well-ventilated working place.
小心火灾或爆炸。
Take precautions of the risks of fire or explosion.
现场遵守一切健康安全规定。
Observe all health and safety regulations on site

提 醒 注 意
Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.
