

**FXHG-309 游艇船底防污漆 (游艇专用)****FXHG-309 Antifouling Paint for Yacht Bottom**

产品特性 Characteristics	由硅烷改性环氧树脂为基料，具有极好的耐水性及憎水性，耐候性及防腐性异常优异 Silane-modified epoxy resin as binder, wonderful water resistance and hydrophobicity, and excellent weather and corrosion resistance.	
	对酸碱盐有非常好的耐受性，耐磨性优异 Very good resistance to acid, alkali and salt, and excellent abrasion resistance.	
	硬度高，对海生物的附着具有排斥性 High hardness with repellency to attachment of marine growths	
产品用途 Uses	主要用于游艇船底的防污及螺旋桨的防锈，也可作为海洋产品的养殖设施的防污使用。 Mainly used for antifouling of yacht bottom and antirust of propeller, also used for antifouling of farming facilities of marine products.	
颜色 Color	铁红色 Iron red	
施工条件 Application conditions	无气喷涂 airless spray 喷嘴尺寸 nozzle size 压力 pressure 稀释比率 dilution ratio 适用于常规的喷涂、刷涂和辊涂	推荐 recommend 0.4~0.5mm 100~150kg/cm <sup>2</sup> 0~5% by wet. (重量比) May be applied by spray, brush, or roller
稀释剂 Thinner	专用稀释剂 Special thinner	
混合比率 Mixing ratio	双组分：主剂/固化剂=4/1 (重量比) Two components: base/hardener=4:1 by weight	
涂装膜厚 Film thickness	干膜: 120μm/道 Dry film thickness 120μm/coat	湿膜:200μm/道 wet film: 200μm /coat
固体含量 Solid content	%	
比重 Specific gravity		
涂覆率 Coverage rate	理论值 : 0.188 千克/平方米/120μm Theoretical: 0.188kg/m <sup>2</sup> /120μm	L/平方米/120μm L/m <sup>2</sup> /120μm
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on surface treatment and environment conditions, and application methods.	



干燥时间 Drying time	温度 Temperature	25°C
	指触干燥 Dry to touch	2hrs
	实干: Dry to handle	24hrs
涂装间隔 Coating interval	Min. 最小 Max. 最大	24hrs —
储存期限 Shelf life	半年 6 months	
包装规格 Package	双组份包装: 25kg 为一组, 组份一为 20kg, 组份二为 5kg 2K packaging: 25kg a kit includes Part A 20kg and Part B 5kg	
表面处理 Surface treatment	用适当的清洁剂和脱脂剂除去油脂 Remove oil thoroughly with suitable detergent or degreaser. 用高压空气吹扫除去灰尘的污物 Remove the contaminants like dust with a high-pressure blower. 施工前确认表面清洁干燥 Confirm the surface clean and dry before application.	
涂装配套 Coating system	适用底材: 金属底材、铝材或玻璃钢 Substrate : metal, aluminum or glass fiber reinforced plastic 适用下涂: 环氧连接漆 Applicable subsequent coat : Epoxy Tie Coat	
安全注意事项 Safety precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Insure adequate ventilation in working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site	
提醒注意 Declaration	本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product	



**JINHAI PAINTS**

津海涂料

---

and its manufacturing process.

---

**TIANJIN JINHAI SPECIAL COATINGS & DECORATION CO., LTD.**