

**ACTH-210 沥青漆（船用）****ACTH-210 Asphalt Paint (For ships)**

产品特性 Characteristics	干燥迅速、良好的光泽和耐候性； Fast drying, high gloss and good weather resistance; 耐机械磨损性、良好的施工性能。 Mechanical abrasion resistance and good workability.		
产品用途 Uses	主要用于各种船舶的船底防腐或大型储罐罐底板下表面和埋地管道的外防腐。 An anticorrosive coating for a variety of ship bottoms or the bottom surfaces of large-scale storage tanks and exterior underground pipelines.		
颜色 Color	黑色、棕色 Black or brown		
施工条件 Application method	无气喷涂 Airless spray	推荐 Recommended	
	喷嘴尺寸 Nozzle tip	0.8~0.9mm	
	压力 Fluid pressure	100~150kg/cm ²	
	稀释比率 Thinning	0~5%	
	适用于无气喷涂、空气喷涂、刷涂及辊涂。以辊涂为佳。 May be applied by spray, brush, or roller, and roller is preferred.		
稀释剂 Thinner	专用稀释剂 Special thinner		
混合比率 Mixing ratio	单组分 One-pack		
涂装膜厚 Film thickness	干膜: 30μm/道 Dry film thickness: 30μm /coat	湿膜: 45μm/道 Wet film thickness: 45μm /coat	
固体含量 Solid content	58%		
比重 Specific gravity	1.35		
涂覆率 Coverage rate	理论值 : 0.09kg/m ² /30μm Theoretical: 0.09kg/m ² /30μm	L/m ² /30μm L/m ² /30μm	
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.		
干燥时间 Drying time	温度 (°C) Temperature (°C)	5	20
	指触干燥 (hrs) Dry to touch (hrs)	5	3
	半硬干燥 (hrs) Semi-dry (hrs)		2



	Dry hard (hrs)	50	25	20
涂装间隔 Coating interval	Min. 最小 (hrs)	50	25	20
	Max. 最大 (hrs)	—	—	—
储存期限 Shelf life	一年 12 months			
包装规格 Packing specification	20kg/桶 20 kg/barrel			
表面处理 Surface preparation	底漆表面应清洁干燥、无污物。 The primer surfaces should be dry, clean and free of any contaminants.			
适用底材 Substrate:	裸钢或沥青底漆 Bare steel or Asphalt Primer.			
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site			
提醒注意 Declaration	本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.			