



FNRH-609 氯化橡胶防腐面漆（各色）

FNRH-609 Chlorinated Rubber Anticorrosive Finishes

产品特性 Characteristics	极好的耐候性 Very good weather resistance. 良好的耐海水飞溅性和耐油性 Good resistance to oil and seawater spattering. 极好的耐磨性 Very good abrasion resistance. 适用于各种涂装配套 Good compatibility with a wide range of coating systems. 干燥迅速 Quick drying.		
产品用途 Uses	主要用于造船工业及沿海钢结构防腐涂装，亦可用于酸厂、碱厂等大型钢铁设施、储罐外的防腐。 Used as anticorrosive coatings for shipbuilding and coastal steel structures, and for the large steel facilities in acid and alkali plant, and for the outside of tanks.		
颜色 Color	白色及各色 White and other colors.		
施工条件 Application method	无气喷涂 Airless spray	推荐 Recommended	
	喷嘴尺寸 Nozzle tip	0.4~0.5mm	
	压力 Fluid pressure	100~150kg/cm ²	
	稀释比率 Thinning ratio	0~5% by weight（重量比）	
	适用于常规的喷涂、刷涂和辊涂 May be applied by spray, brush, or roller.		
稀释剂 Thinner	氯化橡胶稀释剂 Chlorinated rubber thinner		
混合比率 Mixing ratio	单组分 One-pack		
涂装膜厚 Film thickness	干膜: 30μm/道 Dry film thickness: 30μm /coat		
固体含量 Solid content	60%		
比重 Specific gravity	1.2		
涂覆率 Coverage rate	理论值 : 0.1 千克/平方米/30μm Theoretical: 0.1kg/m ² /30μm	0.083L/平方米/30μm 0.083L/m ² /30μm	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.



干燥时间 Drying time	温度 Temperature	10°C	20°C	30°C
	指触干燥 Dry to touch	40mins	30mins	20mins
	实干: Dry to handle:	6hrs	5hrs	4hrs
涂装间隔 Coating interval	Min. 最小 Max. 最大	6hrs —	5hrs —	4hrs —
储存期限 Shelf life	一年 12 months			
包装规格 Packing specification	单组份包装: 20kg/桶 One-component packing: 20 kg/barrel			
表面处理 Surface preparation	底漆表面应清洁干燥, 无污物 The primer surface must be clean, dry and free of any contaminants. 注意施工时与底漆的涂装间隔 Pay attention to the coating interval to the primer during application.			
涂装配套 Coating system	适用下涂: 氯化橡胶防腐底漆、氯化橡胶防腐中层漆或参考我公司的配套 Preferable preceding coat: Chlorinated Rubber Anticorrosive Primer, Chlorinated Rubber Anticorrosive Intermediate Coat, or refer to our coating system.			
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site			
提醒注意 Declaration	本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.			