

**FNRH-502 氯化橡胶水线漆****FNRH-502 Chlorinated Rubber Boot Topping Paint**

产品特性 Characteristics	极好的耐候性、耐海水飞溅性 Excellent weather and seawater resistance. 极好的耐油性、耐磨性 Excellent oil and abrasion resistance 干燥迅速, 适用于各种涂装配套 Quick drying and good compatibility with a wide range of coating systems. 可在-20℃下施工 Can be applied at -20℃.		
产品用途 Uses	主要用于船体的水线部位及船壳、甲板及上层建筑的防腐 An anticorrosive paint for boot top, hulls, decks or superstructures.		
颜色 Colors	灰色 Gray		
施工条件 Application conditions	无气喷涂 Airless spray	推荐 Recommended	
	喷嘴尺寸 Nozzle tip	0.4~0.5mm	
	压力 Pressure	100~150kg/cm ²	
	稀释比率 Thinning ratio	0~5% by weight (重量比)	
	适用于常规的喷涂、刷涂和辊涂 May be applied by spray, brush, or roller.		
稀释剂 Thinner	氯化橡胶稀释剂 Chlorinated rubber thinner		
混合比率 Mixing ratio	单组分 One component		
涂装膜厚 Film thickness	干膜: 30μm/道 Dry: 30μm /coat	湿膜: 60μm/道 Wet: 60μm /coat	
固体含量 Solid content	60%		
比重 Specific gravity	1.25		
涂覆率 Coverage rate	理论值 : 0.1 千克/平方米/30μm Theoretical: 0.1kg/m ² /30μm	L/平方米/30μm L/m ² /30μm	
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.		



干燥时间 Drying time	温度 Temperature	10℃	20℃	30℃
	指触干燥 Dry to touch	40mins	30mins	20mins
	实干: Dry-hard:	6hrs	5hrs	4hrs
涂装间隔 Coating interval	最小 Min. 最大 Max.	6hrs —	5hrs —	4hrs —
储存期限 Shelf life	一年 12months			
包装规格 Packing specification	单组份包装: 20kg/桶 One-component packing: 20 kg/barrel			
表面处理 Surface preparation	底漆表面应清洁干燥, 无污物 The primer surface must be dry, clean and free of any contaminants.			
涂装配套 Coating system	适用下涂: 氯化橡胶铝粉防腐底漆、氯化橡胶防腐铁红底漆或参考我公司的配套。 Subsequent coat: Chlorinated Rubber Aluminum Anticorrosive Primer or Chlorinated Rubber Iron Red Anticorrosive Primer or refer to our coating system.			
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site			
提醒注意 Declaration	本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.			