

**FXH01-4 厚涂型改性环氧防腐底漆（铁红）****FXH01-4 High-Build Modified Epoxy Anticorrosive Primer (Iron Red)**

产品特性 Characteristics	厚涂性重防腐涂料 High-build heavy-duty anticorrosive coating. 极好的耐海水性和耐渗透腐蚀性 Excellent sea water resistance and osmosis corrosion resistance 极好的厚涂施工性 Excellent high built applicability 漆膜坚固、耐磨损 Tough film providing abrasion resistance 对富锌或无锌的环氧底漆附着性非常好 Very good adhesion to zinc-rich or zinc-free epoxy primer 耐重油、原油、脂肪烃溶剂和许多化学物质 Resistance to many chemicals like heavy oil, crude oil, aliphatic solvents etc.			
产品用途 Uses	主要用于裸钢表面，作为底漆防腐使用。 Mainly used as primer for bare steel.			
颜色 Color	铁红 Iron red			
施工条件 Application conditions	无气喷涂 Airless spray	喷嘴尺寸 Nozzle size	压力 Pressure	稀释比率 Dilution ratio
	推荐 Recommended	0.4~0.5mm	100~150kg/cm ²	0~10%by weight（重量比）
	适用于常规的喷涂、刷涂和辊涂 May be applied by spray, brush, or roller.			
稀释剂 Thinner	FXH-4 环氧稀释剂 Epoxy Thinner			
混合比率 Mixing ratio	双组分：主剂/固化剂=8/1（重量比） Double components: base/curing agent=8:1 by weight			
混合使用期 Pot life	温度： Temperature	10℃	20℃	30℃
	混合使用期： Pot life	10hrs	8hrs	6hrs
涂装膜厚 Film thickness	干膜： Dry film thickness:	100μm/道	湿膜： wet film thickness:	185μm/道
		100μm/coat		185μm/coat
固体含量 Solid content	74.2%			
比重 Specific gravity	1.5			



提醒注意

Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.
